

Chemcure R75 & R90

Concrete Curing Membranes

Description

These membranes are formulated with inert hydrocarbon resins which give films with excellent water retention efficiency in excess of 75% and 90% respectively, complying with ASTM C309.66 and HA Spec. clause 1027.

Available in clear, white and with aluminium flake pigment, to give maximum solar reflection.

Independent test reports are available upon request.

Advantages

- Provides a labour saving method of ensuring all fresh concrete is cured properly, without the use of 'ponding' techniques, or the continuous wetting of hessian stretched over the concrete surface.
- Aids concrete to attain maximum hydration, strength, durability and surface hardness.
- A single application only is required.
- Shrinkage associated with hairline cracking and crazing is greatly reduced in both vertical and horizontal applications.
- When used in accordance with the manufacturers instructions the material will disintegrate and flake off from the concrete surface over a period of months depending on the weather conditions and degree of exposure.
- Tested in accordance with BS 7542: 1992.

Technical information

	Chemcure R75	Chemcure R90
Appearance	Amber Liquid	Amber Liquid
Curing Efficiency	≥75%	≥90%
Coverage	4.5-6.0 m ² per litre	4.5-6.0 m ² per litre
Specific Gravity	0.81 @ 20°C	0.86 @ 20°C
Flash Point	47°C -ABEL	47°C -ABEL
Freezing Point	-15°C	-15°C

Application Instructions

On horizontal freshly placed concrete spray Chemcure R at a rate of 4.5 - 6.0 m² per litre immediately after compaction and when surface water has disappeared.

On vertical surfaces, thoroughly dampen with water after stripping, apply Chemcure R at a rate of 4.5 - 6.0 m² per litre using Nufins Metal Spray Equipment. Clean equipment immediately after use with Nuwash.

Packaging

Chemcure R is supplied in 20 litre and 210 litre drums.

Nuwash is supplied in 5 litre and 20 litre containers.

Storage

Material should be stored at normal temperature, out of the reach of children and away from foodstuffs.

Health & Safety

Product Safety Data Sheets (SDS) are available from Nufins. SDS sheets are provided to help customers satisfy their safe handling, use and disposal needs as well as assist with any conformance requirements made locally by health and safety regulations.

SDS are continually updated to provide the very latest information to our customers. We therefore recommend contacting our head office to obtain the most recent and accurate SDS before handling and using any product.

Limitations

Concrete surfaces treated with Chemcure R are not generally suitable for painting, screeding, rendering or application of sealants and adhesives unless the surface membrane has been removed.



Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors. Technical contacts are available to provide further information and arrange demonstrations

