

CURECOTE SUPER

Acrylic Curing Membrane

Description

Curecote Super is a clear styrene acrylic curing and sealing compound designed for application to freshly cast concrete to provide a highly efficient curing membrane. The applied coating remains on the concrete surface to provide a dust free abrasion resistant surface which readily accepts the application of many subsequent finishes. Curecote Super may also be used as a clear sealer on aged concrete to dustproof and provide a surface which is more easily cleaned.

Applications

- Curing agent and sealer for new concrete floors which will subsequently receive a coating.
- Anti-carbonation coating.
- Curing agent for concrete cast from formwork.
- Curing agent and sealer for freshly cast concrete components.

Advantages

- Cures and seals concrete in one application.
- Prevents dusting of concrete surfaces.
- Inhibits efflorescence and acts as an anti carbonation coating.
- Non yellowing and weather resistant.

Technical Information

Viscosity:	15 sec. @ 20°C B4 Ford Cup
S.G.:	0.91
Coverage:	5-6 m ² /litre
Curing Efficiency:	Over 80% efficient when tested to ASTM 309
Recommended Spray	
Pressures:	Typically 50-60 psi (3.3-4.0 BAR) Minimum 40 psi (2.7 BAR)

Application Instructions

Curecote Super should be sprayed onto the concrete surface as soon as possible after any surface water has disappeared at a rate of 5-6 m² per litre.

Application to power floated concrete floors should be carried out after power floating is complete.

Concrete struck from formwork should be dampened down with clean water prior to the application of Curecote Super.

When applied to freshly cast concrete Curecote Super acts as a curing membrane which prevents the loss of water from the concrete surface thus assisting in the efficient hydration of the cement particles.

The application of Curecote Super to fresh concrete will seal and harden the concrete surface whilst acting as an anti-carbonation coating and efflorescence suppressor. Curecote Super is ultra violet resistant, does not degrade and remains as a permanent coating on the concrete surface.

The subsequent application of epoxy, polyurethane, acrylics, vinyls, bitumens and alkyds generally bond well to the Curecote Super treated surface but we would recommend a test area is applied to ensure compatibility of the particular system in question.

On existing concrete surfaces Curecote Super may be applied by brush, spray or roller at a rate of 6-10 m² per litre. One or two coats should be applied depending on the porosity of the concrete and the degree of sealing/dustproofing required.

Packaging

Curecote Super is available in 25 and 210 litre containers.

Storage

Materials should be stored at room temperature protected from frost and kept out of the reach of children.



Health & Safety

Ensure adequate ventilation and do not use near naked flames or smoke during use as the product is inflammable. Avoid contact with skin and eyes.

Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors.

Technical representatives are available throughout the UK to provide further information and arrange demonstrations.



Kingston House, 3 Walton Road, Pattinson North, Washington, Tyne & Wear, NE38 8QA, United Kingdom.

TEL: +44 (0) 191 416 8360 FAX: +44 (0) 191 415 5966 W: www.nufins.com E: info@usluk.com

The information and/or specifications contained herein or in our literature or given by Nufins, its employees, distributors, agents or representatives with regard to its product or their use or application are given in good faith, but no liability is accepted for any loss or damage (including direct or consequential loss or loss of profits) from the use of products because Nufins has no control over how its products are used and applied.