

EPICON DSP

High Performance Surface Primer

Description

Epicon DSP is a solvent free adhesion promoter for use in difficult conditions where a more conventional primer may not give adequate performance, providing a moisture barrier tack coat to green or damp concrete and as an excellent anti-corrosion protection primer for steel.

Applications

- All cementitious substrates including damp/green concrete allowing the application of either epoxy or polyurethane self leveller or screed.
- To allow the early application of methacrylate waterproof coatings.
- Steel.
- Chemical resistant primer.
- Other damp or difficult to wet out substrates.

Advantages

- Provides a barrier between damp or wet surfaces and moisture sensitive finishing coats such as epoxy and polyurethane floor finishes.
- Offers a high degree of anti-corrosion protection.
- Relatively low viscosity with good working properties.
- Outstanding adhesion to damp concrete or sand blasted steel.
- Slight flexibility.

Technical Information

Type:	Solvent free epoxy
S.G.:	1.08
Viscosity:	800-1200 MPa's
Gel Time:	130 minutes @ 20°C
Coverage:	2-3 M ² /kg
Flash Point:	76°C
Storage Temperature:	Between 2-40°C
Dry Film Thickness:	300 micron @ 3 M ² /Kg

Surface Preparation

Concrete surfaces should be clean, free from oil, grease and chemical contamination.

Steel surfaces should be degreased and blasted to SA2¹/₂ to remove rust, scale and oxide layers.

Application of the primer to steel should take place immediately after blasting or within 4 hours.

Mixing

Add the contents of the hardener tin to the base tin and mix thoroughly for approximately 1-3 minutes until homogenous.

Application Instructions

Apply Epicon DSP to the substrate with a stiff bristled brush ensuring that the primer is well worked into the surface. Coverage is 2-3 M² per kilo depending on surface profile.

Allow the primer to become tacky, between 8-24 hours depending on temperature. Once the primer has achieved a tacky state, the subsequent coating/screed should then be applied. Normal application temperature is between 5 and 15°C, higher temperatures will reduce the time in which the overcoating materials can be applied. Should the primer dry on the surface, a further primer coating should be applied, always allow the primer to become tacky before overcoating.

Packaging

Epicon DSP is supplied in 5 kg and 25 kg units.

Storage

Epicon DSP should be stored at normal room temperature. If stored below 10 °C the containers should be warmed prior to use as this will greatly aid the mixing procedure.

Epicon DSP should be stored away from foodstuffs and out of the reach of children.

Health & Safety

Epicon DSP, like similar products, is capable of irritating unprotected skin, we therefore recommend the use of a suitable barrier cream and gloves should be worn.

Technical Support

Through our technical department and laboratories we can offer a comprehensive service to specifiers and contractors.

Technical representatives are available throughout the UK to provide further information and arrange demonstrations.



Kingston House, 3 Walton Road, Pattinson North, Washington, Tyne & Wear, NE38 8QA, United Kingdom.

TEL: +44 (0) 191 416 8360 FAX: +44 (0) 191 415 5966 W: www.nufins.com E: info@usluk.com

The information and/or specifications contained herein or in our literature or given by Nufins, its employees, distributors, agents or representatives with regard to its product or their use or application are given in good faith, but no liability is accepted for any loss or damage (including direct or consequential loss or loss of profits) from the use of products because Nufins has no control over how its products are used and applied.